

# SIATKI DO SITODRUKU

Specyfikacja



Typ	Liczba włókien $\pm 3\%$		Kolor	Rodzaj splotu	Średnica włókna ( $\mu\text{m}$ )	Mesh Opening ( $\mu\text{m}$ )	Prześwit (%)	Grubość ( $\mu\text{m}$ )	Teor. Zużycie farby ( $\text{cm}^3/\text{m}^2$ )
	/cm	/inch							
DDP10	10	25	W	PW	200	816	65	400 $\pm$ 7	260,0
DDP12	12	30	W	PW	140	707	70	270 $\pm$ 7	189,0
DDP12	12	30	W	PW	250	597	50	498 $\pm$ 7	249,0
DDP16	16	40	W	PW	180	455	51	352 $\pm$ 7	179,5
DDP16	16	40	W	PW	200	435	47	385 $\pm$ 7	181,0
DDP20	20	50	W	PW	140	368	52	272 $\pm$ 7	142,7
DDP24	24	60	W	PW	100	323	58	185 $\pm$ 7	107,3
DDP24	24	60	W	PW	120	303	51	220 $\pm$ 7	112,2
DDP24	24	60	W	PW	140	283	45	247 $\pm$ 7	111,2
DDP32	32	80	W	PW	55	263	68	90 $\pm$ 7	61,2
DDP32	32	80	W	PW	64	254	64	107 $\pm$ 7	68,5
DDP32	32	80	W	PW	70	248	61	123 $\pm$ 7	75,0
DDP32	32	80	W	PW	100	218	47	181 $\pm$ 7	85,1
DDP32	32	80	W	PW	120	198	39	223 $\pm$ 7	87,0
DDP36	36	90	W	PW	90	192	46	165 $\pm$ 7	75,9
DDP36	36	90	W	PW	100	182	42	189 $\pm$ 7	79,4
DDP39	39	100	W	PW	55	199	61	98 $\pm$ 7	59,8
DDP39	39	100	W	PW	64	190	56	112 $\pm$ 7	62,7
DDP39	39	100	W	PW	80	174	47	144 $\pm$ 7	67,7
DDP43	43	110	W	PW	80	151	43	140 $\pm$ 7	60,2
DDP47	47	120	W	PW	48	164	60	90 $\pm$ 7	54,0
DDP47	47	120	W	PW	55	157	55	101 $\pm$ 7	55,6
DDP47	47	120	W	PW	64	148	49	112 $\pm$ 7	54,9
DDP48	48	120	W	PW	70	142	45	125 $\pm$ 7	56,3
DDP53	53	135	W	PW	48	140	55	80 $\pm$ 7	44,0
DDP53	53	135	W	PW	55	133	50	102 $\pm$ 7	49,0
DDP53	53	135	W	PW	64	124	44	115 $\pm$ 7	50,6
DDP53	53	135	W	PW	70	118	39	126 $\pm$ 7	49,1
DDP55	55	140	W	PW	64	117	42	105 $\pm$ 7	44,1
DDP59	59	150	W	PW	48	121	51	81 $\pm$ 7	41,3
DDP59	59	150	W	PW	55	114	46	102 $\pm$ 7	46,9
DDP59	59	150	W	PW	64	105	39	114 $\pm$ 7	44,5
DDP64	64	163	W/Y	PW	55	101	42	103 $\pm$ 5	43,3
DDP64	64	163	W/Y	PW	64	92	35	103 $\pm$ 5	36,1
DDP68	68	173	W/Y	PW	55	92	39	102 $\pm$ 5	39,8
DDP72	72	183	W/Y	PW	48	91	43	82 $\pm$ 5	35,3
DDP72	72	183	W/Y	PW	55	84	37	95 $\pm$ 5	35,2
DDP77	77	195	W/Y	PW	55	75	33	100 $\pm$ 5	33,0
DDP80	80	203	W/Y	PW	48	77	38	84 $\pm$ 5	31,9
DDP80	80	203	W/Y	PW	55	70	31	90 $\pm$ 5	27,9
DDP90	90	230	W/Y	PW	48	62	32	85 $\pm$ 5	27,2
DDP100	100	255	W/Y	PW	40	60	36	67 $\pm$ 3	24,1
DDP110	110	280	W/Y	PW	40	51	31	62 $\pm$ 3	19,2
DDP120	120	305	W/Y	PW	31	52	39	47 $\pm$ 3	18,3
DDP120	120	305	W/Y	PW	34	49	35	60 $\pm$ 3	18,2
DDP120	120	305	W/Y	PW	40	43	27	65 $\pm$ 3	17,6
DDP140	140	355	W/Y	PW	31	41	32	49 $\pm$ 3	15,7
DDP140	140	355	W/Y	PW	34	38	28	61 $\pm$ 3	14,6
DDP150	150	380	W/Y	PW	31	36	29	49 $\pm$ 3	14,2
DDP150	150	380	W/Y	PW	34	33	24	53 $\pm$ 3	12,7
DDP165	165	420	W/Y	PW	31	29	23	52 $\pm$ 3	12,0
DDP180	180	450	W/Y	PW	27	28	28	45 $\pm$ 3	10,3

